

Product Data Sheet

BG-LL 22B03

Linear Low Density Polyethylene, Film

Applications:

- High stiffness blown & cast film
- Blending
- Lamination

Additives

- Acid scavenger
- Antioxidants
- Lubricant

Feature

- Comonomer:butane-1(c4)
- High stiffness

Resin properties	unit	Condition	Typical value	Test method
Melt index	g/10 min	190°C/2.16 kg	2.8-3.2	ASTM D1238
Density	g/l	23°C	0.920-0.924	ASTM D1505
F/E Ratio	-		<30	ASTM D1238
Yellowness Index	-		0.5	ASTM D1925
Ti content	ppm wt		2	MTM 15636
Fish Eyes	Gels/m2	-	60-100	MTM 17108
Haze	%		2	ASTM D1003
Gloss 45°	%O		90	ASTM D2457
Dart impact	gr		70	ASTM D1709
Tensile modulus	2% sec	MD	115	ASTM D882
	Mpa	TD	120	ASTM D882
	Ultimate	MD	50	ASTM D882
Tensile strength	Mpa	TD	24	ASTM D882
	@Break	MD	480	ASTM D882
Elongation	%	TD	850	ASTM D882
		MD	90	ASTM D1922
Elmendorf tear	g	TD	350	ASTM D1922

Density: 0.920 - 0.924 MFI: 2.8 - 3.2